

Technical Data Sheet

EnDURO Classic 200 J

Description

Laminate: Paper - (PP)Film - Paper.
80-40-80

Applications

- ◆ Textile tags
- ◆ Tickets

Printability

EnDURO can be printed in offset, flexo and rotogravure.
You need only standard printing inks.

Paper Properties

Weight	:	205 ± 20	g/m ²	ISO 536
Thickness	:	215 ± 15	µm	ISO 534
Tensile Strength	MD :	> 200	N/15mm	ISO 1924
	CD :	> 180	N/15mm	
Stiffness	MD :	> 950	mN	DIN 53 121 15°/10mm
	CD :	> 450	mN	
Brightness (+457)	:	> 85	%	ISO 2470
Opacity	:	> 96	%	ISO 2471

Storage & Converting

For quality reasons EnDURO should be stored originally packed.
Storage & converting conditions of 20±5°C and 50±10% rel. humidity are recommended.

We always recommend comprehensive testing of materials prior to regular conversion.

All information is based on current quality level. We reserve the right to change this as part of our continual product development.
Any guarantee of product characteristics or suitability for specific application requires separate written confirmation from Sihl.

Status: January 2009

Please, always ask for the latest data sheet.

