

Technical Data Sheet

EnDURO Effect M-60 YP silver

Description

Laminate: Paper - (PP)Film - Paper.
20-20-20

Applications

- Book-pages for high-value or frequently used books
- Book-jackets / dust covers
- Tags

Special Features

- Silvery appearance
- High opacity
- Tear-resistant and safe
- Dimensional stability

Printability

EnDURO can be printed in offset, flexo and rotogravure.
You need only standard printing inks.

Paper Properties

Weight	:	65	±	7	g/m ²	ISO 536
Thickness	:	85	±	7	µm	ISO 534
Tensile Strength	MD :	>	50		N/15mm	ISO 1924-3; 300mm/min
	CD :	>	50		N/15mm	
Stiffness	MD :	>	30		mN	DIN 53 121; 15°/10mm
	CD :	>	15		mN	
Brightness (+457)	:	>	70		%	ISO 2470-1
Opacity	:	>	98		%	ISO 2471

Storage & Converting

For quality reasons EnDURO should be stored originally packed.

Storage & converting conditions of 20±5°C and 50±10% rel. humidity are recommended.

We always recommend comprehensive testing of materials prior to regular conversion.

All information is based on current quality level. We reserve the right to change this as part of our continual product development.
Any guarantee of product characteristics or suitability for specific application requires separate written confirmation from Sihl.



Sihl GmbH, Düren Tel.: +49 (0)2421-597-0 E-Mail: info@sihl.de
ISO 9001 - ISO 14001 - OHSAS 18001 approved