

Preliminary Technical Data Sheet

EnDURO Classic Plus 190 G

Description

Laminate: Paper - (PP)Film - Paper.
70-40-70

Applications

- ◆ Textile tags
- ◆ Entrance tickets
- ◆ Tickets

Special Features

- ◆ Smooth top and reverse side

Printability

EnDURO can be printed in offset, flexo and rotogravure.
You need only standard printing inks.

Paper Properties

Weight	:	appr. 185	g/m ²	ISO 536
Thickness	:	appr. 170	µm	ISO 534
Tensile Strength	MD :	> 180	N/15mm	ISO 1924-3; 300mm/min
	CD :	> 150	N/15mm	
Stiffness	MD :	> 600	mN	DIN 53 121 15°/10mm
	CD :	> 300	mN	
Brightness (+457)	:	> 90	%	ISO 2470-1
Opacity	:	> 92	%	ISO 2471

Storage & Converting

For quality reasons EnDURO should be stored originally packed.

Storage & converting conditions of 20±5°C and 50±10% rel. humidity are recommended.

We always recommend comprehensive testing of materials prior to regular conversion.

All information is based on current quality level. We reserve the right to change this as part of our continual product development.

The information given in this datasheet is provisional and temporary and is not binding as the product remains in development stages.

Values provided are relevant to previous productions and may not be representative of all future makings.

Status: November 2009

Please, always ask for the latest data sheet.

