

Technical Data Sheet

PicoFilm P-275 M2

Description

PicoFilm P-275 M2 is a white PET-Film, coated on both sides with a matt primer.

Applications

- ◆ Tags for outdoor applications

Special Features

- ◆ V.I.P. printable (see below)
- ◆ Temperature resistant
- ◆ Suitable for outdoor use

Printability

Can be printed on:

- ◆ Flexo-, Letterpress-, Offsetprinting (sheets only).
- ◆ with UV- or conventional drying process

Physical Properties

Weight		360 ± 10	g/m ²	ISO 536
Thickness		275 ± 10	µm	ISO 534
Stiffness	M.D.	~ 1500	mN	DIN 53 121, 15°/10mm
	C.D.	~ 2000	mN	
Tear strength	M.D.	590 ± 30	N/15mm	ISO 527-1 250mm/min
	C.D.	550 ± 30	N/15mm	
Elongation at break	M.D.	280 ± 50	%	ISO 527-1 250mm/min
	C.D.	290 ± 50	%	
Opacity		> 98	%	ISO 2471

Suitability for V.I.P (Variable Information Printing)

Laser : Yes, with b/w and 4c laser printer.
Thermal Transfer : Yes, with wax, resin/wax and resin ribbons.
Others : Dot matrix, pen and pencil

Storage & Converting

For quality reasons PicoFilm should be stored originally packed.
Storage & converting conditions of 23±5°C and 50±10% rel. humidity are recommended.

We always recommend comprehensive testing of materials prior to regular conversion.

All information is based on current quality level. We reserve the right to change this as part of our continual product development.
Any guarantee of product characteristics or suitability for specific application requires separate written confirmation from Sihl.

Status: March 2009

Please, always ask for the latest data sheet.

